

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
27 September 2001 (27.09.2001)

PCT

(10) International Publication Number
WO 01/70897 A2

(51) International Patent Classification⁷: C09J 7/00

(21) International Application Number: PCT/US01/09113

(22) International Filing Date: 20 March 2001 (20.03.2001)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
09/532,576 22 March 2000 (22.03.2000) US

(71) Applicant: **THE PROCTER & GAMBLE COMPANY**
[US/US]; One Procter & Gamble Plaza, Cincinnati, OH
45202 (US).

(72) Inventors: **HAMILTON, Peter, W.**; 1107 Devils Backbone Road, Cincinnati, OH 45233 (US). **MCGUIRE, Kenneth, S.**; 15 Linden Drive, Wyoming, OH 45215 (US). **POLAND, James, Edward**; 1321 Amsterdam Road, Park Hills, KY 41011 (US). **BOUTHILET, Andrew, L.**; 585 Terrace Avenue, Cincinnati, OH 45220 (US).

(74) Agents: **REED, T., David et al.**; The Procter & Gamble Company, 5299 Spring Grove Avenue, Cincinnati, OH 45217-1087 (US).

(81) Designated States (*national*): AE, AG, AL, AM, AT, AT (utility model), AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, CZ (utility model), DE, DE (utility model), DK, DK (utility model), DM, DZ, EE, EE (utility model), ES, FI, FI (utility model), GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SK (utility model), SL, TJ, TM, TR, TT, TZ, UA, UG, UZ, VN, YU, ZA, ZW.


(84) Designated States (*regional*): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).

Published:

— without international search report and to be republished upon receipt of that report

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: HIGH BOND STRENGTH, REPOSITIONABLE ADHERENT SHEET



(57) Abstract: An adherent sheet material and method of making including at least one adhesive, non-raised region protected from inadvertent adherence to a contact surface. This adherent sheet material also including a film having a front face and back face, wherein the front face has a plurality of collapsible, non-adhesive protrusions extending outwardly from the front face and adhesive, non-raised region disposed between the protrusions. Also, a substrate is bonded to the back face of film. An adherent sheet material including a contact adhesive protected from inadvertent adherence to a contact surface. This adherent sheet material also including a film having a front face and back face, wherein the front face has a plurality of collapsible, non-adhesive protrusions extending outwardly from the front face and adhesive, non-raised region disposed between the protrusions. The film also includes a number density of protrusions from about 50 protrusions per square inch of the film to about 150 protrusions per square inch of the film. Also, the contact adhesive is disposed upon non-raised regions.

HIGH BOND STRENGTH, REPOSITIONABLE ADHERENT SHEET

FIELD OF THE INVENTION

5 The present invention relates to flexible sheet materials having an adhesive for providing a high bond strength and having outermost surface features for preventing premature adhesion to an contact surface such as a target surface. Even more particularly, the present invention relates to repositionable wall covering, tapes, labels, etc. comprising a flexible film having protrusions that act to space an adhesive from a target surface until the wall covering is pressed thereagainst.

BACKGROUND OF THE INVENTION

Decorative sheet-like materials, such as wall coverings are well known in the art. Such sheet materials are generally formed of paper, plastic, metal foil, fabric material or some combination thereof having a pattern or design printed or embossed on the front surface, with the back surface being coated by the user with an adhesive, such as glue, cement, or the like (generally known as "wallpaper paste") by which the wall covering may be bonded to a wall, ceiling or other target surface.

20 Other types of wall coverings include those having a plastic decorative surface and a backing of woven or non-woven fabric or paper. The back surface is adapted to be coated by the user with the adhesive set forth above in order to secure the wall covering to a surface. However, users dislike the inconvenience of mixing and applying the paste. Additionally, there are prepasted wall coverings available. However, these prepasted wall coverings need a water trough and this can be both time consuming and messy. Also, both the non-prepasted and prepasted wall coverings require the user to perform additional steps to apply the wall covering to the target surface. Generally, once these conventional wall coverings are applied to the target surface, only slight adjustments in their position upon the target surface may be made before the adhesive cures.

To eliminate the additional steps and mess of using "wallpaper paste", wall coverings have attempted to use pressure sensitive adhesives. Pressure sensitive adhesives are known to provide immediate adhesion between two materials upon

contact. Such adhesives rely on quick set-up reaction or rapid cure time for prompt adhesion. In the art of tapes, labels, wall coverings and other articles using pressure sensitive adhesives to adhere an adhesive coated surface to a target surface, there has been recognized the problem of premature adhesion or sticking to contact surfaces, such as a target surface. That is, before the adhesive coated surface can be properly positioned over a target surface, inadvertent contact of the adhesive with the target surface causes premature adhesion at one or more locations, thereby inhibiting proper positioning. For example, due to this premature sticking to the target surface, wall coverings are very difficult to apply to a wall and then reposition, as occurs when lining up the patterns of at least two wall covering sheets.

To reduce this premature adhesion to contact surfaces, pressure sensitive adhesive wall coverings have typically used adhesives with a low bond strength or tack to attach it to the target surface. However, this creates an additional problem in that the wall coverings lack sufficient tack to maintain attachment to the target surface for long periods of time. Because of this low tack, over a period of time the user experiences the wall covering peeling from the wall especially at the sheet margins.

However, pressure sensitive adhesives ("PSA") with a higher bond strength or tack, i.e., aggressive or permanent pressure sensitive adhesives, generally have not been used to combat the problem of insufficient tack. This is due to the fact that these permanent PSA's are very tacky and tenacious and thus become very difficult to handle and use. For example, the wall covering will prematurely adhere to contact surfaces, such as the user's hands or the target surface. Once the adhesive has made premature contact with the surface, the user generally cannot remove the wall covering or even make slight adjustments in its position without destroying the wall covering or significantly reducing the bond strength. Therefore, most PSA wall coverings use low tack PSA's in an attempt to make the wall coverings easy to use. However, as mentioned above, even these low tack PSA's can cause the problem of premature adhesion to a contact surface. Although the user can generally separate the low bond strength wall covering from the contact surface without destroying the wall covering, it still frustrates the user and wastes the user's time.

Others have tried to solve the problem of premature adhesion to contact surfaces by applying a removable release paper to the adherent sheet material such as found for example in U.S. Patent No. 5,487,929 issued to Rusincovitch, Jr. et al. on January 30, 1996. However, this release paper adds additional costs to the sheet material and requires both the manufacturer and user to perform additional steps. Others have also tried to solve the specific problem of premature adhesion of a adherent, decorative sheet material by placing solid protrusions as spacers between the decorative sheet and the target surface such as also found in U.S. Patent No. 5,487,929, issued January 30, 1996, to Rusincovitch, Jr. et al. However, these protrusions are solid and thus require more material and do not completely collapse.

Still others have tried to solve the problem of premature adhesion of an adherent sheet material to contact surfaces by placing spacers to separate the pressure sensitive adhesive from the target surface, such as found, for example, in U.S. Patent No. 4,376,440 to Whitehead et al., U.S. Pat. No. 5,141,790 to Calhoun et al., U.S. Pat. No. 4,959,265 to Wood et al., U.S. Pat. No. 5,344,693 to Sanders, U.S. Pat. No. 4,061,820 to Magid et al., and European Patent Application No. 0 623 332 A1 to Lauritzen. Generally, this art has focused on the use of stand-offs with pressure sensitive adhesives primarily in the area of sanitary napkins. However, different solutions are needed for flexible, adherent sheet materials having protrusions intended to be adhered to smooth or rigid surfaces. Commonly assigned, U.S. Patent Nos. 5,662,758 issued to Hamilton et al. on September 2, 1997, and 5,871,607 issued to Hamilton et al. on February 16, 1999, provide a thorough description of the art in adherent sheets protected from premature adhesion and are herein incorporated by reference.

Both of these commonly assigned patents involve adherent sheets which are protected from premature adhesion to a contact surface via hollow protrusions. However, generally, neither deal with wall coverings, labels or other adherent sheet materials having protrusions with either an additional substrate or a high bond strength.

It is well known in the art to bond a substrate to a flat film such as by laminating the two together using pressure and a laminating adhesive. However, if the film is formed with hollow protrusions then a problem exists in how to combine the substrate with the film that has hollow protrusions without crushing the film protrusions. Additionally, once the substrate is bonded to the film, an additional problem of air entrapment within the protrusions is created. For example, the substrate and potentially the laminating adhesive may now have created a gas barrier that prevents air from escaping from the protrusions when the protrusions are made to collapse. If the air does not escape from the protrusion, the protrusion may not fully collapse and thus prevent full adhesion of the sheet material to the target surface.

U.S. Patent No. 5,906,883, issued May 25, 1999, to Blanc-Brude, discusses plurality of interconnected non-adherent elements made from a substrate. However, it is believed that this requires a difficult process to make.

Therefore, such adherent sheet materials leave room for improvement in ease of use and manufacture, cost, repositionability and bond strength.

Accordingly, it would be desirable to provide an improved multi-layered, adherent sheet material which is inexpensive to make, has means for protecting the adhesive from prematurely adhering to contact surfaces yet is efficient to store and ship.

It would also be desirable to provide such a material which is easily handled and manipulated by a user during the application process and is repositionable, yet forms an adequate bond with a variety of materials and surfaces to effectively adhere to the target surface.

It would also be desirable to provide a wall covering which is easily handled and manipulated by a user during the application process and is repositionable, yet forms an adequate bond against a variety of materials and surfaces to effectively adhere to the target surface.

35

SUMMARY OF THE INVENTION

An adherent sheet material including at least one adhesive, non-raised region protected from inadvertent adherence to a contact surface. This adherent sheet material also including a film having a front face and back face, wherein the front face has a plurality of collapsible, non-adhesive protrusions extending outwardly from the front face and adhesive, non-raised region disposed between the protrusions. Also, a substrate is bonded to the back face of film.

An adherent sheet material including at least one adhesive, non-raised region protected from inadvertent adherence to a contact surface. This adherent sheet material also including a film having a front face and back face, wherein the front face has a plurality of collapsible, non-adhesive protrusions extending outwardly from the front face and adhesive, non-raised region disposed between the protrusions. The film also includes a number density of protrusions from about 10 protrusions per square inch of the film to about 175 protrusions per square inch of the film. The adherent sheet material has a peel force of at least about 0.3 pounds per linear inch.

An adherent sheet material including a contact adhesive protected from inadvertent adherence to a contact surface. This adherent sheet material also including a film having a front face and back face, wherein the front face has a plurality of collapsible, non-adhesive protrusions extending outwardly from the front face and adhesive, non-raised region disposed between the protrusions. The film also includes a number density of protrusions from about 50 protrusions per square inch of the film to about 150 protrusions per square inch of the film. Also, the contact adhesive is disposed upon said non-raised regions.

Also included in the present invention is a method for making an adherent sheet material having a film with protrusions, a contact adhesive protected from inadvertent adherence and a substrate bonded to the film. The sheet being adherable to a target surface only when pressed thereagainst. The method includes coating a forming drum with a contact adhesive. The forming drum has a top surface, wherein this surface has a plurality of recesses therein. This coating step applies the contact adhesive to the top surface without bridging the recesses. The next step in the method is placing a piece of flexible film in contact with the contact adhesive on the top surface of the forming drum. The contact adhesive

will preferentially adhere to the piece of flexible film. Then, a piece of flexible film is formed to create a plurality of protrusions extending into the recesses of the forming drum. The plurality of protrusions being registered with the contact adhesive. Also, a substrate is coated with a laminating adhesive and placed in
5 contact with a back face of the film. After this step, the substrate and the film are joined with pressure to form a bonded layer. Finally, the piece of sheet material is removed together with the pressure sensitive adhesive from the forming drum.

BRIEF DESCRIPTION OF THE DRAWINGS

10 While the specification concludes with claims particularly pointing out and distinctly claiming the present invention, it is believed that the present invention will be better understood from the following description in conjunction with the accompanying Drawing Figures, in which like reference numerals identify like elements, and wherein:

15 Figure 1 is a cross-sectional view of a adherent sheet material embodiment of the present invention;

Figure 2 is a top planar view of the adherent sheet material shown in Figure 1;

Figure 3 is a cross-sectional view of a adherent sheet material shown in
20 Figure 1 in contact with a contact surface;

Figure 4 is a cross-sectional view of a preferred adherent sheet material embodiment in contact with a contact surface;

Figure 5 is a cross-sectional view of a adherent sheet material shown in Figure 4 in contact with a contact surface, wherein a force (F) has been applied to
25 adherent sheet material causing protrusions to collapse;

Figure 6 is an alternative embodiment of a adherent sheet material of the present invention, wherein the lamating adhesive follows the contours of the protrusion along the back face of the film;

Figure 7 is an alternative embodiment of a adherent sheet material of the
30 present invention, wherein the laminating adhesive is discontinuous;

Figure 8 is an alternative embodiment of a adherent sheet material of the present invention, wherein the film is apertured;

Figure 9 is process flow chart of a method for making the composite sheet material of the present invention, disclosing a automated embossing process to
35 form sheet material of the present invention;

Figure 10 is a side elevation view of the nip region of the method for making the composite sheet material of the present invention; and

Figure 11 is a side elevation view of the pressure drum and the female embossing drum, wherein the substrate is bonded to the formed film having protrusions of the present invention.

DETAILED DESCRIPTION OF THE INVENTION

Referring now to the drawings, and more particularly to FIGS. 1-8, there is shown a preferred embodiment of the present invention, which provides the adherent sheet material and is generally indicated as 10. As shown in FIG. 1 (cross-sectional view), adherent sheet material 10 includes a piece of a flexible film sheet 20 having an operational front face 22, a back face 24, non-adhesive, three-dimensional protrusions 26 extending outwardly from the front face 22 and adhesive, non-raised regions 28 located between the protrusions 26.

Sheet material 10 is a selectively-activatable, adhesive-bearing structure which bonds sheet material 10 to a target surface. The target surface for the adhesive system includes but is not limited to walls, table tops, shelves, etc.

As utilized herein, the term "selectively-activatable" is used to refer to materials which exhibit substantially non-adherent properties when brought into contact with target surfaces until some action is taken by a user to "activate" the material to reveal adhesive properties. Accordingly, selectively-activatable properties differ from permanently-active strips of adhesive which rely upon removal of liner materials (typically silicone-coated paper strips or films) to expose the adhesive for use.

Selective activation of such materials allows the user to properly position sheet material 10 upon a target surface before activation and adhesion are accomplished, as well as minimizing the likelihood of contamination of the adhesive system before use. This characteristic permits the sheet material 10 to be manipulated in any desired mode without encountering the difficulties of premature adhering of the adherent sheet to itself or to other contact surface 50s, and without the need for separate release sheets, liners, microspheres or the like

which often need to be removed prior to contact with the target surface. If desired, the selective activation process may be temporary, i.e., minimal contact between adherent, non-raised regions 28 and a contact surface 50 for evaluation of sheet material's 10 position upon target surface and then may be de-activated without destroying sheet material 10 for either removal of sheet material 10 from or repositioning it upon target surface 50 for further use without significant loss of adhesive capability.

Regardless of the manner of activation, materials useful as an adhesive system in accordance with the present invention will exhibit an adhesive, adherent or tacking character as opposed to merely a clinging or affinity character. As utilized herein, the terms "adhesive" is utilized to refer to the ability of a material to exhibit an adherent character whether or not it actually includes a composition commonly understood and labeled as an adhesive. Accordingly, such materials will form a bond or seal when in contact with itself or another target surface as opposed to merely being attracted to such surface. While a number of approaches such as the use of selectively adherent materials may be utilized to provide the desired adhesive properties, a presently preferred approach is to utilize a pressure sensitive adhesive.

When designing materials useful as an adhesive system in accordance with the present invention, it may be desirable to tailor the particular choice of adhesive material or agent so as to provide either a permanent bond or a releasable bond as desired for a particular application. In accordance with the preferred embodiment of the present invention, depending upon extent of the activation employed, the sheet 10 can demonstrate a releasable bond, i.e., a temporary bond, be either removed without destroying sheet material 10 or repositioned and then activated completely once placed in desired position upon target surface to form a permanent bond between sheet 10 and target surface.

Referring to FIGS. 1-3, sheet material 10 includes adhesive, non-raised regions 28 on film sheet 20 between and around protrusions 26. Adhesive, non-raised regions 28 have adhesive properties which can be achieved in a variety of different ways. One such way to provide non-raised regions 28 adhesive characteristics is to fabricate film sheet 20 from a material that demonstrates

5 adhesive characteristics, including but not limited to plasticized polymers, i.e., polyvinyl chloride, silicones, hydrogels, polyvinylidene dichloride, Kraton Rubber, urethane polymers, plastisols, plasticized waxes, i.e., organic waxes (beeswax), inorganic waxes (paraffin), etc., gelatins and other organic based, proteinaceous materials.

10 Also, Commonly assigned, U.S. Patent Application No. 08/745,340, filed November 8, 1996 in the name of Hamilton et al. describes materials that exhibit adhesive or "cling" properties and is herein incorporated by reference. As
15 discussed above, such materials can exhibit adhesive or "cling" properties on a constant basis, such that they cling to themselves and to other surfaces whenever brought into proximity with them, whether desirable or not. Such materials often incorporate resins, additives, tackifiers, or other materials to achieve the target level of cling. Suitable methods of measuring and quantifying this cling property
20 are described in ASTM test methods D5458-95 and D3354-89. Test method D5458-95 is useful for measuring cling between two layers of film in both stretched and unstretched conditions, and utilizes a 1 inch wide film strip adhered to a flat film attached to an inclined surface. The force required to remove the film strip from the flat film is measured. Test method D3354-89 is useful for
25 measuring the degree of blocking (unwanted adhesion) existing between overlapping layers of plastic film. Film-to-film adhesion is expressed as a blocking load in grams which will cause two layers of film to separate with an area of contact of 100 square centimeters.

25 Another such way to provide the non-raised regions 28 adhesive characteristics is to fabricate film sheet 20 from materials with activated adhesive systems, including but not limited water activated adhesives, ultraviolet light activated systems, encapsulated adhesive, anaerobic, i.e., cyanoacrylates.

30 Again, referring to FIGS. 1-3, a third way to provide non-raised regions 28 of film sheet 20 with adhesive characteristics is to dispose upon or coat on a surface of non-raised regions 28, preferably a contact adhesive 12, including but not limited to a pressure sensitive adhesive ("PSA").

Generally, the pressure sensitive adhesive (PSA) useful in the invention can be any adhesive known to those skilled in the art, including but not limited to elastomeric-type PSAs comprising natural rubber, reclaimed rubber, styrene-isoprene-styrene rubber, butadiene-acrylonitrile rubber, polyvinyl ether rubber, 5 styrene-butadiene-styrene rubber, butyl rubber, polyisobutylene rubber, nitrile rubber, styrene-butadiene rubber, polyurethane, polysulfide, polyesters, silicone resins and gums, neoprene rubber, acrylic, methacrylic, polyacrylate ester rubber, and vinyl and mixtures thereof.

10 Contact adhesive 12 is preferably a pressure sensitive adhesive, also preferably a hot melt adhesive, most preferably an adhesive of specification number X 801 334 03, made by Ato Findley Co. of Wauwatosa, Wisconsin. Contact adhesive 12 may be refastenable, releaseable, permanent, or otherwise. The size, shape and spacing of protrusions 26 is preferably selected to provide a 15 continuous contact adhesive 12 path surrounding protrusions 26 but is not necessary to practice the invention and thus a discontinuous adhesive path could be applied upon non-raised regions 28. Contact adhesive layer 12 has a thickness of X which is preferably from about 0.001 inches to 0.010 inches, most preferably 0.002 inches of pressure sensitive adhesive.

20 If film sheet 20 is fabricated from a material having adhesive properties in order to provide non-raised regions 28 an adhesive property, then protrusions 26 being made of the same material would need some type of non-adhesive coating ("cappers") to permit sheet material 10 to slide or be repositioned over contact 25 surface 50. The cappers can be applied minimally over protrusion apex 27 of protrusions 26, preferably the entire surface of each of protrusions 26. These cappers demonstrate non-adhesive properties and include but are not limited to silicones, inorganic powders, i.e., talc, powdered mica, calcium carbonate, etc., inks and other non-tacky coatings well known in the art. These non-adhesive 30 cappers, prevent the activation of film sheet's 20 adhesive properties, thus permitting repositionability and preventing premature adhesion to a contact surface 50 of sheet 10.

If film sheet 20 is fabricated from a material having adhesive properties 35 that require an intentional activation to activate the adhesive properties of the

material, then protrusions 26 do not require any type of non-adhesive, coating or cap. The user will selectively activate only the adhesive properties of adhesive, non-raised regions 28 and not the adhesive properties of non-adhesive, protrusions 26.

5

Still referring to FIGS. 1-3, film sheet 20 is preferably fabricated from a polymer that does not have adhesive characteristics, which may be made from homogeneous resins or blends thereof. Single or multiple layers within the film structure are contemplated, whether co-extruded, extrusion-coated, laminated or
10 combined by other known means. Useful resins include, but are not limited to, polyethylene (PE), polypropylene (PP), polyethylene terephthalate (PET), polyvinyl chloride (PVC), polyvinylidene chloride (PVDC), latex structures, nylon, etc. Polyolefins are generally preferred due to their lower cost and ease of forming but are not necessary to practice the invention. High density
15 polyethylene (HDPE) is most preferred to fabricate the film sheet. Other suitable materials to fabricate the film from include, but are not limited to, aluminum foil, coated (waxed, etc.) and uncoated paper, coated and uncoated wovens, scrims, meshes, nonwovens, and perforated or porous films, and combinations thereof. In a particularly preferred embodiment, the flexible film sheet material is a formed
20 film from about 0.0001 inch to about 0.005 inches, more preferably about 0.001 inch thick film.

Protrusions 26 are discreet, collapsible three-dimensional outermost surface features formed from film sheet 20. Protrusions 26 extend outwardly from
25 the front face 22 in a substantially perpendicular direction, occupying a voided space 25 under protrusions 26 (FIG. 1). Protrusions 26 have heights (H) which are preferably less than their diameters D1, so that when they collapse, they collapse along an axis which is substantially perpendicular to a plane of sheet 10. This mode of collapse avoids protrusions 26 folding over and blocking adhesive
30 12 from contact with a target surface 50. Commonly assigned, U.S. Patent Nos. 5,662,758 issued to Hamilton et al. on September 2, 1997, and 5,871,607 issued to Hamilton et al. on February 16, 1999, and commonly assigned, U.S. Patent Application Nos. 08/745,340, filed November 8, 1996 in the name of Hamilton et al. and 09/369,743, filed August 6, 1999 in the name of Hamilton et al. provide

detailed information on adherent sheets having formed film sheets with protrusions and are herein incorporated by reference.

Protrusions 26 are collapsible in that they are hollow protrusions that, once
5 placed under a significant applied pressure, deform from a substantially three-
dimensional structure (as shown in FIG. 1) to a substantially two-dimensional
structure (as shown in FIG. 5). The term "discreet" is used herein to refer to the
fact that film sheet 20 separates voided spaces 25 of each protrusion 26, i.e.,
protrusions 26 are not interconnected to any other individual protrusion 26. In
10 other words, the air entrapped within the voided space 25 of one of protrusion 26
cannot travel to any of the other protrusions 26.

Protrusions 26 are preferably domed-shaped but can be a variety of shapes
without changing the scope of the invention, such as conical, cylindrical,
15 hemispherical, toroidal and pyramidal. Preferably, protrusions 26 have a
protrusion apex 27 which is a point on protrusions 26 having the greatest
perpendicular distance from the front face 22 of the film sheet 20.

The number density of protrusions 26, i.e., the number of protrusions per
20 square inch, is an important parameter in the context of the present invention
because it is one determination of the compressive strength of protrusions 26. The
term "compressive strength" is used herein to refer to a perpendicularly applied
force (F) a particular three-dimensional sheet can support for a given amount of
sheet deflection. For this particular case, protrusion 26 deflection is analogous to
25 sheet deflection. This information is important because it quantifies the
perpendicularly applied force (F) required to deform a particular sheet to a given
protrusion height H. Protrusion height (H) is defined as the perpendicular
distance from the front face 22 of the film 20 to the protrusion apex 27. For
example, from Figure 1, if a thickness (X) of adhesive 12 is coated across the
30 front face 22 of the film sheet 20 such that it fills the adhesive, non-raised regions
28 between protrusions 26, the force (F) could be determined that would deform
the sheet 10 to the height (X) of the adhesive 12, thus exposing the adhesive 12 to
the contact surface 50.

35

COMPRESSIVE STRENGTH ANALYTICAL TEST METHOD

This test was used to determine the compressive strength of the film sheet 20 at different levels of protrusion 26 deformation.

5

A circular sample with a diameter of 0.8 inches was cut from the film sheet material. The circular sample was then placed on the lower, stationary platform of an INSTRON brand model 8511 compression tester (available from INSTRON Corporation, Caston, Mass.). The upper moveable platform of the 10 compression tester was then lowered until it barely came in contact with the sheet's protrusions. The three-dimensional sample was then fully compressed into a substantially two-dimensional sheet at an upper platform rate of 0.05 pounds per second. The compression tester was operated by the INSTRON Plus 8500 display unit in load control running from 0 to 10 pounds. Displacement of the upper 15 platform and compressive load were measured and recorded throughout the test on an oscilloscope.

Based upon this test method, the present invention had a compressive strength of at least about 0.1 pound per square inch, preferably of at least about 1 20 pound per square inch, more preferably from about 0.5 pounds per square inch to about 15 pounds per square inch, even more preferably from about 3 pounds per square inch to about 10 pounds per square inch before contacting adhesive, non-raised regions 28, preferably contact adhesive 12..

25 Referring to FIGS. 1 and 2, the protrusions 26 have a protrusion height (H) preferably from about 0.01 inches to about 0.1 inches, more preferably 0.015 inches to about 0.040 inches, even more preferably 0.020, most preferably 0.025 inches and a base surface area from about 0.001 square inches to about 0.0065 square inches, most preferably 0.004 square inches. In the preferred embodiment, 30 the base surface area (SA) is calculated by the formula of $SA = \frac{1}{4}\pi (D1)^2$. In a even more preferred embodiment, protrusions 26 have a base diameter (D1) from about 0.030 inches to about 0.10 inches, more preferably from about 0.040 inches to about 0.09 inches, most preferably 0.070 inches. Center-to-center spacing (C) of protrusions 26 can be randomly spaced using the method described in 35 commonly assigned, U.S. Patent No. 5,965,235, issued to McGuire et al. on

October 12, 1999, and herein incorporated by reference. FIG. 2 shows a preferred embodiment in which center-to-center spacing (C) is uniformly spaced, more preferably from about 0.05 inches to about 0.15 inches, even more preferably from about 0.07 inches to about 0.115, most preferably 0.105 inches.

5

FIGS. 3 and 4 show a contact surface 50, which may be smooth and rigid and is typically non-deformable, being spaced away from layer of contact adhesive 12 by protrusions 26. Contact surface 50 is defined as a surface generally parallel to front face 22 of film sheet 20 which contacts the protrusions 26 preferably at their protrusion apex 27. Contact surface 50 can be a variety of surfaces which sheet material's 10 adhesive layer 12 could come in contact with, such as a user's hand, drum, rollers, the sheet material itself and target surfaces such as walls, table tops, shelves, windows, etc.

15

Film protrusions 26 prevent the contact adhesive 12 from contacting any contact surfaces until the film 20 is intentionally pressed against desired contact surface 50, i.e. target surface 50. The adherent sheet material 10 is applied to contact surface 50 wherein the film protrusions 26 make contact with contact surface 50 and thus protect the contact adhesive 12 from contacting contact surface 50. The protrusions 26 prevent the premature adhesion of the adherent sheet 10, such as a wall covering, from prematurely adhering to the contact surface 50. This also permits the user to position sheet material 10 upon target surface 50 and then reposition, i.e., slide, sheet 10 to another position numerous times without destroying sheet material 10 or substantially reducing contact adhesive's 12 tack.

25

In particular, FIG. 4 shows a preferred embodiment of adherent sheet material 10 further consisting of a substrate 40 bonded to back face 24 of film sheet 20. This substrate 40 may be bonded to the back face 24 of the film sheet 20 by any type and method that suits the needs of the application. For example, they may be bonded together by way of heat-sealing, ultrasonic welding, preferably a laminating adhesive 30, including but not limited to slot coating and spray coating, , etc., most preferably spray coating.

30

Especially useful but not necessary for this lamination is a tacky PSA, including but not limited to all the PSA's mentioned in the detailed description of contact adhesive 12 set forth above. The protrusion's 26 tendency to rebound to its' undeformed height can cause the sheet 20 to lose some or all of its' adherence to the target surface 50, but when a pressure sensitive adhesive 30 is used between the adherent sheet 20 and the substrate 40, the PSA 30 serves to help maintain the protrusions 26 in a collapsed state due to the adherence of the adhesive layer 30 to the collapsed protrusion 26 as shown in Fig. 5. Similarly, when a pressure sensitive adhesive 30 is applied to the back face contours of protrusions 26 in an alternative embodiment shown of Fig. 6, the same advantageous effect will be realized. The substrate 40 may be made of a variety of materials currently used as wall coverings, including but not limited to flexible and partially non-flexible foils, fabric, plastic films, and papers.

FIG. 5 also shows protrusions 26 collapsed under a force as indicated by force (F), applied to back face 24 of film sheet 20,. Once protrusions 26 collapse, non-adhesive region 28, preferably contact adhesive 12, is caused to adhere to contact surface 50. This adhesion can be permanent or temporary depending upon how many protrusions 26 were collapsed. For example, if only a minimal number of protrusions are collapsed, sheet 10 will temporarily bond to target surface 50 because only a small percentage of contact adhesive 12 is adhered to contact surface 50. This temporary adhesive state allows the user to evaluate the position of sheet material 10 upon target surface 50 for only a very short time period; and if it is not in a desired position, remove sheet material from target surface and reposition it upon the target surface 50. When the user has found the final position of the wallpaper, a compressive force is applied to entire substrate 40 substantially perpendicular to a plane of sheet 10, thus deforming film protrusions 26. This exposes the adhesive 12 to the target surface 50 and thus preferably provides a permanent adherence for sheet material 10. The substrate 40 is then the outermost layer and may contain a decorative pattern such as is found in wall coverings. This sheet material 10 may be combined as a kit with instructions for use, consisting of the following instructions:

(a) positioning sheet material 10 on target surface 50 with front face 22 in contact with surface 50, until sheet material 10 is in desired location upon target surface 50; and

(b) applying a force (F) perpendicular to and across the substrate sufficient to collapse the collapsible protrusions 26, whereby the contact adhesive 12 comes in contact with the surface 50.

5 In an alternative embodiment, a low tack contact adhesive, including but not limited to low tack PSA's, can be applied to the protrusion "tips" or protrusion apex 27. This low tack PSA would provide enough tack to hold sheet 10 to target surface 50 temporarily, but protrusions 26 would still prevent target surface 50 from contacting adhesive, non-raised regions 28, preferably contact adhesive 12, 10 which consists of a high tack adhesive. Again, once sheet material 10 is position (and repositioned) upon target surface 50, a perpendicular force (F) applied to entire back face 24 of film sheet 20 will collapse protrusions 26 and permanently bond sheet material 10 to target surface 50.

15 In the preferred embodiment, once the adherent sheet 20 has been selectively activated, it has a peel force of at least about 0.3 pounds per linear inch, preferably at least about 0.5 pounds per linear inch, most preferably a peel force from about 0.5 pounds per linear inch to about 0.9 pounds per linear inch. The term "peel force" is used herein to refer to the force (F) required to peel the 20 adherent system, i.e., sheet 10, from a contact surface 50, i.e., target surface 50, in a substantially perpendicular direction from target surface 50. The peel strength, i.e., peel force, of the adhesive is preferably measured by Pressure Sensitive Tape Council Method PSTC-1. A 12 inch (30.5 cm) long by 1 inch (2.5 cm) wide strip of film is rolled once against a smooth stainless steel surface at a rate of 12 inches 25 (30.5 cm) per minute using a 4.9 pound (2.25 kg) roller and then tested as having an average adhesion value of greater than about 0.3 pounds per linear inch (pli).

When bonding substrate 40 to film sheet 20, substrate 40 will act as a gas barrier, entrapping the air in voided space 25 of protrusions 26, if certain 30 precautions are not taken. This entrapped air can be problem because the air, if not allowed to escape, can prevent protrusions 26 from completely collapsing. There are a variety of ways to approach solving this potential problem of air flow management. The term "air flow management" as used herein refers to the many different ways of providing a path or channel so that the air entrapped within 35 voided space 25 can escaped as protrusions 26 are being collapsed. These air vent

paths or channels can be at a macroscopic or microscopic level and either intentionally formed or naturally occurring within film sheet 20, substrate 40 or laminating adhesive 30, either singly or in combination.

To incorporate the air vent channels in sheet material 10, film sheet 20, substrate
5 40 or laminating adhesive 30, either singly or in combination can be porous, permeable, perforated, discontinuous or apertured.

The term "porous" is used herein to refer to the ability of a material to admit fluids, preferably gas, to pass through its pores or interstices. The term
10 "permeable" is used herein to refer to the ability of material to admit fluids, preferably gas, to pass through its pores or interstices whether intentionally induced or naturally occurring within the material. The term "perforated" is used herein to refer to a plurality of holes punched in a material. The term
15 "discontinuous" is used herein to refer to the intentional use or application of a material that is not a continuous layer of material such that the material does not form a barrier layer to the gas escaping voided space 25 of protrusions 26 when protrusions 26 are collapsed. The term "apertured" is used herein to refer to any hole, slit or opening of any size or shape intentionally formed within such materials.

20

In a preferred embodiment depicted in FIG. 4, the laminating adhesive 30 and substrate 40 should be either porous, permeable, perforated, discontinuous, apertured or some combination thereof, thereby permitting the protrusions 26 to collapse more completely by displacing any air trapped in the voided volume 25
25 of the protrusions 26 through the air vent channels within the laminating adhesive 30 and/or substrate 40. For example, one embodiment of the present invention includes both a substrate 40 and laminating adhesive 30 that are either porous or permeable. In another embodiment, both substrate 40 and laminating adhesive 30 are perforated under protrusions 26 such that entrapped air in void space 25 can
30 escape through the perforated air vent channels.

In an alternative embodiment depicted in FIG. 6, substrate 40 is either porous, permeable, perforated, discontinuous, apertured or some combination thereof and laminating adhesive 30 follows the contours of protrusions 26 along back face 24
35 of film sheet 20 forming non-adhesive regions under protrusions 26. This

embodiment does not require adhesive 30 to be discontinuous or permeable to permit protrusions 26 to more completely collapse. In yet another embodiment of sheet material 10, laminating adhesive 30 may be discontinuous by microscopic channels imparted in it by the spray coating process. The laminating adhesive 30
5 may also be discontinuous by way of macroscopic channels formed by the periodic application of laminating adhesive 30 upon substrate 40 forming a non-continuous path as shown in Fig. 7.

In yet another embodiment of sheet material 10, film sheet 20 is porous, permeable, perforated, discontinuous or any combination thereof and substrate 40
10 can be gas impermeable or include any of the above mentioned properties to provide additional air vent channels. Other alternative embodiments which allow for trapped air to be displaced from the voided volume 25 of the protrusions 26 through film sheet 20 include, but are not limited to, intentionally permeable sheet material, such as found in paper sheets, breathable sheets (additive), etc.

15
FIG. 8 shows another alternative embodiment wherein protrusions 26 are apertured on front face 22, as well as the back face 24, of the film sheet 20 forming an opening at protrusion apex 27. Having the protrusions 26 open on both the front face 24 and back face 24 allows for the air trapped in the voided
20 volume 25 of the protrusions 26 to be displaced along a contact surface when compressed.

A method of making is illustrated in Figure 9. The film sheet 20 may be formed by vacuum thermoforming or embossing or other means as shown and described
25 in commonly assigned, U.S. Patent Nos. 5,662,758 issued to Hamilton et al. on September 2, 1997, and 5,871,607 issued to Hamilton et al. on February 16, 1999, and commonly assigned, U.S. Patent Application Nos. 09/289,222, filed April 9, 1999 in the name of McGuire et al. which are herein incorporated by reference. Embossing is the preferred method of making the adherent sheet material 10 and
30 is set forth below.

FIGS. 9-11 show an automated process for making sheet material 10, generally indicated as 60. A drum 64 (hereinafter referred to as "female embossing drum"
64) has an outermost diameter that has patterned depressions. This outermost
35 diameter is treated to have a low surface energy, i.e., a release coating is applied,

so that the adhesive 12 will not readily wet it, or in other words, the adhesive 12 will have a greater affinity to the film sheet 20 than the female embossing drum 64. This outermost diameter is then coated with the adhesive 12 by an adhesive deposition system 62 such that the adhesive 12 is only transferred to the
5 outermost diameter of the female drum 64 and is not transferred into the patterned depressions. This adhesive deposition drum 62 is positioned upstream from the female embossing drum 64 and a matching drum 68 with matching patterned male drum pins (hereinafter referred to as "male embossing drum" 68). The male
10 embossing drum 68 is mated with the female embossing drum 64 such that each of the male drum pins on the male embossing drum 68 has a corresponding depression in the female embossing drum 64 into which it engages at a nip region 70.

Automated process 60 introduces a film sheet 20 into this nip region 70 whereby it
15 is permanently, mechanically deformed by the matching set of embossing drums (64 and 68), and their corresponding male drum pins and female drum depressions as shown in FIG. 10. The deformation is such that film sheet 20 retains the three-dimensional shape of the male drum pins of the male embossing drum 68 even after film sheet 20 has left the nip region 70. The film sheet 20 may be preheated
20 to aid in such permanent deformation by radiant heating, conductive heating, convective heating or other methods well known in the art.

At the nip region 70, in addition to being permanently mechanically deformed by the embossing drums, the film sheet 20 also comes in contact with the adhesive 12
25 that is coated only on the outermost diameter of the female embossing drum 64. Due to the pre-coating on the outermost diameter of the female drum 64, the adhesive adheres itself to the film sheet 20 in the spaces 28 between and around the film protrusions 26 that are formed through permanent mechanical deformation by the embossing drums. This results in a three-dimensional formed
30 film sheet 20 with a layer of adhesive 12 surrounding embossed, film stand-off protrusions 26 that have a greater height H than the thickness of the adhesive X.

A method of bonding a film sheet 20 and a substrate 40 to each other is shown in
Figures 9 and 11. While the formed film sheet 20 is still integrally connected with
35 the female embossing drum 64, a substrate 40 is laid on the side of the film sheet

20 not in contact with the female embossing drum 64. Before contact with the film sheet 20, a laminating adhesive 30 is deposited on the substrate 40 by a substrate adhesive deposition system 72 by slot coating, or other methods well known in the art. While using a pressure sensitive laminating adhesive 30 is the preferred method to create the bond between the film and the substrate, other methods, such as heat sealing or ultra-sonic welding may also be used. After initial contact between the film sheet 20 and the substrate 40, or at the point of contact, the film sheet 20 and substrate 40 are joined by pressure from a pressure drum 74, in a direction perpendicular to the plane of the film sheet 20 at that point. Since the formed film sheet 20 is still integrally connected with the female embossing drum 64 when the film sheet 20 and substrate 40 are combined by the pressure drum 74, the film protrusions 26 are protected from deformation under the pressure of the pressure drum 74 by the patterned depressions in the female embossing drum 64. These patterned depressions effectively surround the film protrusions 26, thereby serving as a protective shell that prevents the pressure drum 74 from collapsing the film protrusions 26. The substrate 40 and film 20, which are now bonded together, are then stripped from the female embossing drum 64 by a stripping drum 76.

The protrusion size, shape and spacing, the film flexural modulus, and the film thickness determine the resistance of the protrusions to collapse over a unit area. It is desirable to provide a strength which is sufficient to withstand a pressure up to about 4.4 pounds per square inch without collapsing protrusions to where the adhesive contacts a target surface. This resistance to collapse enables the composite material to be wound onto a drum without damage for compact packaging purposes and to be handled and repositioned without premature adherence to a target surface. A composite material having the most preferred dimensions is believed to provide the desired strength. While particular embodiments of the present invention have been illustrated and described, it will be obvious to those skilled in the art that various changes and modifications may be made without departing from the spirit and scope of the invention, and it is intended to cover in the appended claims all such modifications that are within the scope of the invention.

WHAT IS CLAIMED IS:

1. An adherent sheet material characterized by at least one adhesive, non-raised region protected from inadvertent adherence to a contact surface, characterized by:
5 a film having a front face and back face, said front face having a plurality of collapsible, non-adhesive protrusions extending outwardly from said front face and said adhesive, non-raised region disposed between said protrusions; and
a substrate layer bonded to said back face of film.
2. A sheet material according to claim 1, further characterized by a contact adhesive disposed upon said non-raised regions.
3. A sheet material as in any of the previous claims, characterized in that a compressive force of at least about 6.89×10^3 dyne per square centimeter (0.1 psi) is required to collapse said protrusions.
4. A sheet material as in any of the previous claims, further characterized by a number density of protrusions from about 4 protrusions per square centimeter (10 protrusions per square inch) of said film to about 69 protrusions per square centimeter (175 protrusions per square inch of film).
5. A sheet material as in any of the previous claims, further characterized in that said air venting channel is at least one aperture disposed within a plurality of said protrusions.
6. An adherent sheet material comprising at least one adhesive, non-raised region protected from inadvertent adherence to a contact surface, characterized by:
a film having a front face and back face, said front face having a plurality of collapsible, non-adhesive protrusions extending outwardly from said front face and said
5 adhesive, non-raised region disposed between said protrusions, said film having a number density of protrusions from about 4 protrusions per square centimeter (10 protrusions per

square inch) of said film to about 69 protrusions per square centimeter (175 protrusions per square inch) of said film; and

10 further characterized by said adhesive non-raised region having a peel force of at least about 53.6 grams per lineal centimeter (0.3 pounds per linear inch).

7. A sheet material according to claim 6, further characterized by a substrate layer bonded to said back face.

8. A sheet material according to either of claims 6 and 7, further characterized in that a compressive force of at least about 6.89×10^3 dyne per square centimeter (0.1 psi) is required to collapse said protrusions.

9. An adherent sheet material comprising a contact adhesive protected from inadvertent adherence to a contact surface, characterized by:

5 a film having a front face and back face, said front face having a plurality of collapsible protrusions extending outwardly from said front face and non-raised regions disposed between said protrusions; and

said adhesive disposed upon said non-raised regions, said film having a number density of protrusions from about 20 protrusions per square centimeter (50 protrusions per square inch) of said film to about 59 protrusions per square centimeter (150 protrusions per square inch) of said film.



10. A method for making an adherent sheet material having a film with protrusions, a contact adhesive protected from inadvertent adherence and a substrate bonded to said film, said sheet being adherable to a target surface only when pressed thereagainst, said method characterized by the steps of:

5 a) coating a forming drum with a contact adhesive, said forming drum having a top surface, said top surface having a plurality of recesses therein, said coating step applying said contact adhesive to said top surface without bridging said recesses;

7995/JB

- 10 b) placing a piece of flexible film in contact with said contact adhesive on said top surface of said forming drum, said contact adhesive preferentially adhering to said piece of flexible film;
- c) forming said piece of flexible film to create a plurality of protrusions extending into said recesses of said forming drum, said plurality of protrusions being registered with said contact adhesive;
- d) coating said substrate with a laminating adhesive;
- 15 e) placing said substrate in contact with a back face of said film, wherein said laminating adhesive coating said substrate contacts said back face of said film;
- f) joining said substrate and said film with pressure to form a bonded layer; and
- g) removing said piece of sheet material together with said pressure sensitive adhesive from said forming drum.

1/5



2/5




Fig. 3




Fig. 4

3/5




Fig. 5




Fig. 6

SUBSTITUTE SHEET (RULE 26)

4/5




Fig. 7




Fig. 8




Fig. 9

5/5




Fig. 10




Fig. 11

SUBSTITUTE SHEET (RULE 26)

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
27 September 2001 (27.09.2001)

PCT

(10) International Publication Number
WO 01/70897 A3

(51) International Patent Classification⁷: C09J 7/02, B32B 3/00, B44C 1/10, B05D 5/10

(21) International Application Number: PCT/US01/09113

(22) International Filing Date: 20 March 2001 (20.03.2001)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
09/532,576 22 March 2000 (22.03.2000) US

(71) Applicant: **THE PROCTER & GAMBLE COMPANY**
[US/US]; One Procter & Gamble Plaza, Cincinnati, OH 45202 (US).

(72) Inventors: **HAMILTON, Peter, W.**; 1107 Devils Backbone Road, Cincinnati, OH 45233 (US). **MCGUIRE, Kenneth, S.**; 15 Linden Drive, Wyoming, OH 45215 (US). **POLAND, James, Edward**; 1321 Amsterdam Road, Park Hills, KY 41011 (US). **BOUTHILET, Andrew, L.**; 585 Terrace Avenue, Cincinnati, OH 45220 (US).

(74) Agents: **REED, T., David et al.**; The Procter & Gamble Company, 5299 Spring Grove Avenue, Cincinnati, OH 45217-1087 (US).

(81) Designated States (*national*): AE, AG, AL, AM, AT, AT (utility model), AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, CZ (utility model), DE, DE (utility model), DK, DK (utility model), DM, DZ, EE, EE (utility model), ES, FI, FI (utility model), GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SK (utility model), SL, TJ, TM, TR, TT, TZ, UA, UG, UZ, VN, YU, ZA, ZW.

(84) Designated States (*regional*): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).

Published:

— with international search report

(88) Date of publication of the international search report:
7 March 2002

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: **HIGH BOND STRENGTH, REPOSITIONABLE ADHERENT SHEET**

(57) Abstract: An adherent sheet material and method of making including at least one adhesive, non-raised region protected from inadvertent adherence to a contact surface. This adherent sheet material also including a film having a front face and back face, wherein the front face has a plurality of collapsible, non-adhesive protrusions extending outwardly from the front face and adhesive, non-raised region disposed between the protrusions. Also, a substrate is bonded to the back face of film. An adherent sheet material including a contact adhesive protected from inadvertent adherence to a contact surface. This adherent sheet material also including a film having a front face and back face, wherein the front face has a plurality of collapsible, non-adhesive protrusions extending outwardly from the front face and adhesive, non-raised region disposed between the protrusions. The film also includes a number density of protrusions from about 50 protrusions per square inch of the film to about 150 protrusions per square inch of the film. Also, the contact adhesive is disposed upon non-raised regions.

INTERNATIONAL SEARCH REPORT

International Application No
PCT/US 01/09113

A. CLASSIFICATION OF SUBJECT MATTER

IPC 7 C09J7/02 B32B3/00 B44C1/10 B05D5/10

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 C09J B32B B44C B05D

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

WPI Data, PAJ, EPO-Internal

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	EP 0 708 162 A (MINNESOTA MINING & MFG) 24 April 1996 (1996-04-24) claim 1 example 1 figure 1 column 7, line 25 - line 45	6,8,9
X	US 5 906 883 A (BLANC-BRUDE DOMINIQUE) 25 May 1999 (1999-05-25) cited in the application figure 2 column 2, line 23 - column 3, line 3 -/--	1-3

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents:

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

- *T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- *X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- *Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- *Z* document member of the same patent family

Date of the actual completion of the international search

1 October 2001

Date of mailing of the international search report

10/10/2001

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Schlicke, B

INTERNATIONAL SEARCH REPORT

International Application No

PCT/US 01/09113

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	<p>EP 0 393 953 A (MINNESOTA MINING & MFG) 24 October 1990 (1990-10-24) cited in the application example 1 examples 4,10 tables I-III</p>	1-10

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/US 01/09113

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
EP 0708162	A	24-04-1996	US 5589246 A	31-12-1996
			DE 69514885 D1	09-03-2000
			DE 69514885 T2	05-10-2000
			EP 0708162 A2	24-04-1996
			JP 8183933 A	16-07-1996
US 5906883	A	25-05-1999	EP 0894644 A1	03-02-1999
EP 0393953	A	24-10-1990	US 4959265 A	25-09-1990
			AU 613553 B2	01-08-1991
			AU 5140190 A	18-10-1990
			BR 9001729 A	04-06-1991
			CA 2012561 A1	17-10-1990
			DE 69004144 D1	02-12-1993
			DE 69004144 T2	19-05-1994
			EP 0393953 A2	24-10-1990
			ES 2045801 T3	16-01-1994
			JP 2298569 A	10-12-1990
			JP 2603743 B2	23-04-1997
			ZA 9002283 A	28-12-1990